

ABSTRACT OF DISCLOSURE

A silicon film provided on a blocking film 102 on a substrate 101 is made amorphous by doping Si⁺, and in a heat-annealing process, crystallization is started in parallel to a substrate from an area 100 where lead serving as a crystallization-promoting catalyst is introduced.